POLYMETAL LODE

Prince of Wales Island

Alaska



Location of POLYMETAL LODE

ASSAYS from Ketchikan Assay Office

Sample No.	Width	Au.-Oz.	Ag.-Oz.	Pb.-%	Zn.-%
HMF-12	10'	Nil	Trace	5.2	13.2
HMF-13	10'	Nil	Nil	1.1	9.05
HMF-14	20'	0.01	Nil	0.3	2.2
HMF-15	Grab	0.01	0.50	3.1	21.1

Scale : 1" = 40'

40 0 40 80

Brunton-Paulin Altimeter Survey

Territorial Department of Mines
Juneau, Alaska

Sketch by: Howard M. Fowler
Associate Mining Engineer

Date: December 27, 1948