



ANALYSES OF SAMPLES TAKEN AT RUSH AND BROWN MINE BY SOLAR DEVELOPMENT COMPANY
(Furnished by Consolidated Mining and Smelting Co. of Canada, Ltd.)

Sample number	Vein width in feet	Copper in percent	Silver in ounces	Gold in ounces	Sample number	Vein width in feet	Copper in percent	Silver in ounces	Gold in ounces
1		1.06	TR.	TR.	101	FW.	3.48	.29	.17
2	3	2.54	.46	.06	102	5	2.08	.76	.04
3	2	8.48	1.40	.32	103	8 x 6	1.86	.34	.10
4	3	4.31	.84	.06	104	1½	2.95	.46	.06
5	2½	1.72	.54	.04	105	1½	1.32	.30	.35
6	4	.98	.24	.02	106	0.9	13.78	1.90	.56
7	2	2.73	.55	.13	107		.36	TR.	.02
8	1½	4.80	.94	.36	108	3	.34	TR.	.01
9	2½	3.90	1.02	.26	109	2	.20	TR.	TR.
10	3	1.41	.44	.06	110	2½	22.88	3.55	.09
11	3	1.00	.43	.05	111	2½	1.78	.10	.04
12	5	.22	TR.	TR.	112	1	.37	.18	.02
13	3	6.72	1.45	.19	113	5	TR.	TR.	TR.
14	2	16.24	2.80	.26	114	4	.48	.10	.01
15	2	5.36	.97	.27	115	1	.36	TR.	.01
16	1	5.98	1.47	.39	116	2	NIL.	TR.	TR.
17	4	.72	.19	.05	117	3	TR.	TR.	TR.
18	4	2.00	.54	.06	118	4	NIL.	TR.	TR.
19	4	4.96	.87	.05	119	5	TR.	TR.	TR.
20	4	1.86	.52	.04	120	3	.67	.10	.01
21	5	4.92	.65	.09	121	3	.20	TR.	TR.
22	2	6.78	.66	.30	122	4	3.77	.62	.14
23	3	.74	.20	.02	123	3	2.19	.40	.12
24	2	4.15	.76	.40	124	4	1.60	.30	.04
25	3	8.54	1.41	.21	125	3½	1.72	.10	.04
26	3	2.86	.53	.37	126	½	7.36	1.66	.20
27	2	7.40	1.40	.18	127	4	1.64	.40	.08
28	4	8.26	1.56	.32	128	4	NIL.	TR.	TR.
29	4	10.20	1.66	.14					
30	4	8.81	1.46	.10					
31	2	.38	.17	.03					
32	3	.42	.14	.04					
33	3	.84	.17	.05					
34	3	1.08	.18	.02					
35	3	5.98	1.25	.19					
36	2	1.15	.34	.02					
37	1	.64	.10	.02					
38	3	.52	.14	.02					
39	3½	.90	.31	.03					
40	3	1.06	TR.	.03					
41	2	.38	TR.	.02					
42	2	.75	.19	.05					
43	3½	1.00	.19	.05					
44	2½	1.90	.48	.02					
45	2	3.74	.62	.22					
46	2	8.08	2.44	.22					
47	3	7.02	1.24	.26					
48	1½	5.21	1.40	.24					
49	2	8.02	2.23	.17					
50	5	1.74	.54	.10					
51	7	5.12	1.28	.08					
52	2	2.76	.80	.16					
53	3	1.70	.10	.03					
54	2	8.41	.87	.05					
55	3	.58	TR.	TR.					
56	6	1.04	.10	.04					
57	6	3.76	.85	.09					
58	5	3.94	1.04	.10					
59	1½	10.06	1.60	.10					
60	4	4.79	1.16	.08					
61	4	2.00	.66	.06					
62	2	7.16	2.00	.30					
63	4	5.02	.81	.09					
64	2½	3.94	.73	.17					
65	5	3.28	.74	.22					
66	2	.87	.12	.04					
67	3	.14	TR.	.01					
68	1	11.72	2.08	.02					
69	3	6.88	.82	.20					
70	2½	3.14	.52	.20					
71	4	3.52	.43	.05					
72	2½	2.20	.27	.05					
73	1½	7.18	1.31	.11					
74	3	4.60	.70	.14					
75	3	3.66	.77	.09					
76	1½	9.30	1.79	.11					
77	3	2.91	.78	.06					
78	4	1.96	.36	.04					
79	2½	4.10	.88	.28					
80	3	9.36	1.19	.13					
81	6	.06	TR.	TR.					
82	4	.18	TR.	TR.					
83	4	.11	TR.	TR.					
84	4	.12	TR.	.01					
85	4½	2.56	.86	.14					
86	4	5.64	.96	.24					
87	4½	5.50	1.14	.30					
88	5	11.18	1.42	.16					
89	4	4.15	.87	.25					
90	4	14.32	2.10	.18					
91	4	7.42	1.32	.30					
92	4	1.95	.30	.04					
93	3	.96	.28	.02					
94	2	4.60	.59	.17					
95	2½	20.05	1.86	.12					
96	3	5.58	.64	.14					
97	3½	3.58	.54	.26					
98	2½	6.42	.82	.08					
99	2	5.02	.50	.16					
100	1½	3.80	.86	.14					



Modified from map by Solar Development Co.
Published by permission of Consolidated Mining
and Smelting Co. of Canada, Ltd

SECTION ON VEIN OF RUSH AND BROWN MINE, SHOWING LOCATIONS OF SAMPLES



553851 O - 61 (In pocket)