

ALASKAN GEOLOGY BRANCH
TECHNICAL DATA FILE

Table 12. Rare metal content of minerals from contact rocks and beryllium lodes.

[Analysts: J. C. Hamilton, Barbara Tobin, A. L. Sutton, U. S. Geological Survey] ^{1/}

Minerals from contact zones		Be	Sn	W	Li	B	Cu	Pb	Zn	As	Nb	Purity ^{2/}
Lab. No.	Field No.	Sample type and location										
D112109	63-ASn-7	.005	.02	0	N.D.	.15	.0001	.001	.03	0	0	Pure
D112111	63-ASn-15	.05	.07	0	N.D.	.1	.001	.001	.05	0	.001	Pure
D112110	63-ASn-14	.0003	.3	0	N.D.	0	.0	.001	0	0	.005	Pure
Minerals from beryllium-fluorite ores												
D110348	62-ASn-RRG1	.5	.05	.01	.2	1.0	.002	.07	.05	.1	0	Small amount of black opaque
D110349	62-ASn-RRG2	.7	.05	0	.2	.7	.003	.05	.05	.1	0	Small amount of black opaque
D110350	62-ASn-413	.3	.07	.015	.07	5.	.0007	0	0	0	0	Essentially pure
D110352	62-ASn-TC43	.07	.05	.1	.5	.07	.0003	.003	0	0	0	Estimated 99% pure
D110351	62-ASn-413D	7.	.7	0	.07	.5	.003	.003	0	0	.005	Pure
D113993	62-ASn-TC40A	.7	.07	0	.07	.1	.0005	.01	0	0	0	Pure

^{1/} Semiquantitative spectrographic analyses

^{2/} By X-ray diffractometer pattern

^{3/} In oblique reflected light, shows both clear grains and curdy amorphous grains